



GPSS AP 1038

General Purpose Polystyrene for
Extrusion and Molding

Product description:

General purpose polystyrene GPSS AP 1038 is manufactured by continuous mass polymerization of styrenemonomer.

It is a crystal-like , its suitable for use on its own or in blends with impact poly styrene both for extrusion and injection molding.

Typical applications:

It is recommended for manufacture of packaging applications and house hold applications and petri dishes
And XPS sheets and plates

Typical data:

properties	unit	value	ASTM method
physical			
Melt flow rate @200 C & 5 kg load	g/10min	3.1	D1238
Mechanical properties			
Tensile strenght	Mpa	55	D638
Flexural modulus	Mpa	3100	D790
Charpy impact strength	Kj/m ²	10	D256
Thermal properties			
Vicat softening point @120 C,1 kg(min)	C	101	D1525

Note: All mechanical properties measured under standard conditions 50% RH and 23C.

Packing:

GPSS AP 1038 is supplied in the form of cylindrical of approximately 2.5×2.5 mm. the material can be supplied in either 25 kg bags.

Regulatory information:

It is responsibility of the manufacturers of food contact articles and industrial food packers to make sure the article in their actual use are in compliance with the imposed migration requirements.

Edit date: 01/06/2022